

LOCTITE®



LOCTITE 3D 3860™

HDT180 High Temperature
Photoplastic
Black

LOCTITE®

Henkel Corporation

loctite3dp@henkel.com



LOCTITE®

3860™

HDT180 HIGH TEMPERATURE
PHOTOPLASTIC
BLACK



LOCTITE 3D IND3860™

LOCTITE 3D 3860 is a rigid resin that withstands high temperature stress and it is ideal for applications where high resolution and high HDT is required

Printed articles made from LOCTITE 3D 3860 exhibit high heat deflection temperature (HDT) and good print resolution.

LOCTITE 3D 3860 is a low viscosity liquid, printable at room temperature across various DLP Platforms.



Benefits:

- No deformation, more durable
- Survives longer to temperature stress
- Easy to print with high print resolution



Ideal for:

- Functional prototyping
- Encapsulation
- Mounts and housings



Markets:



Industry



Automotive

Tensile Stress at Break (MPa)

39

Young's Modulus (MPa)

3500

Elongation at Failure (%)

2

HDT at 0.455 MPa (°C)

>200

100

Shore Hardness (D)

80

100

**Values shown are linked to LOCTITE 3860 Black as reference, please refer to the specific mechanical properties for each of the colors shown in this document*



LOCTITE®

3860™

HDT180 HIGH TEMPERATURE
PHOTOPLASTIC
BLACK



PROPERTIES

Mechanical Properties	Measure	Method	Green	Post Processed
Tensile Stress at Break	MPa	ASTM D638	35	39
Young's Modulus	MPa	ASTM D638	1800	3500
Elongation at Failure	%	ASTM D638	4	2
Flexural Modulus	MPa	ASTM D790	-	3190 ± 60 [1]
Flexural Stress at Break	MPa	ASTM D790	-	40.0 ± 4.0 [1]
Flexural Strain at Break	%	ASTM D790	-	1.2 ± 0.1 [1]
Shore Hardness	D	ASTM D2240	-	80

Other Properties

HDT at 0.455 MPa	°C	ASTM D648	-	>200 [2]
HDT at 1.82 MPa	°C	ASTM D648	-	166 ± 5 [2]
Thermal conductivity	mW/(m·K)	ASTM D5930	-	193
Specific heat capacity	J/(g·K)	ASTM D5930	-	1.21

Liquid Properties	Measure	Method	Value
Viscosity at 25°C (77°F)	mPa·s	ASTM D7867	400
Liquid Density	g/cm ³	ASTM D1475	1.1

"All specimen are printed unless otherwise noted. All specimen were conditioned in ambient lab conditions at 19-23C / 40-60% RH for at least 24 hours." ASTM Methods: D638 Type IV, 5mm/min, D790-B, 2mm/min, D256 Notched IZOD (Machine Notched), 6 mm x 12 mm, D648, D2240, Type "D" (0, 3 seconds), D570 0.125" x 2" Disc 24hr@ 25°C, D7867@ 25°C (77°F), D1475

Internal Data Sources:

[1] FOR175733 [2] FOR176283



LOCTITE®

3860™

HDT180 HIGH TEMPERATURE
PHOTOPLASTIC
BLACK



WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/printer-validation-settings>

PRINTER SETTINGS

LOCTITE 3D 3860 BK is formulated to print optimally on industrial DLP printer. Read the safety data sheet carefully to get details about health and safety instructions. Recommended print parameters:

- Shake resin bottle well before usage
- Temperature: 20°C to 35°C
- Intensity: 3 mW/cm² to 7 mW/cm²

Exposure time for an intensity of 5 mW/cm²

Layer Thickness (µm):	25	50	100	Ec (mJ/cm ²)	9.08
First layer time (s)	Available upon request			Dp (mm):	0.162
Burn in region (s):					

CLEANING

LOCTITE 3D 3860 BK requires post processing to achieve specified properties. Prior to post curing, support structures should be removed from the printed part, and the part should then be washed. Use compressed air to remove residual solvent from the surface of the material between intervals.

Post Process Step	Agent	Method	Duration	Intervals	Additional Info
Cleaning	IPA	Ultrasonic	1-2 min	1-2	
Dry	n.a.	Compressed air	20 s	1	Air pressure (20 psi)
Wait before post curing	n.a.	Ambient condition	60 min	1	Room temperature



LOCTITE®

3860™

HDT180 HIGH TEMPERATURE
PHOTOPLASTIC
BLACK



WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/printer-validation-settings>

POST CURING

LOCTITE 3D 3860 BK requires post curing to achieve specified properties. It is recommended that either an LED or wide spectrum lamp be used to post cure parts.

UV Curing Unit	UV Source	Intensity	Cure time per side	Additional Settings (Shelf, Output Energy)
Loctite – CL36	LED 405 nm	85 mW/cm ²	20 min	100% Top and Side

LOCTITE 3D 3860 BK requires a **thermal curing cycle** after UV post curing to achieve specified properties. It is recommended to place parts in an unheated oven. Heat up to 160°C to cure the parts for 30 minutes. Switch off oven and allow parts to cool down in oven to prevent stress and warpage.

STORAGE

Store LOCTITE 3D 3860 BK in the unopened container in a dry location. Optimal Storage: 8°C to 30°. Storage below 8°C or above 30°C can adversely affect product properties. Material removed from containers may be contaminated during use. For this reason, filter used resin with 190µm mesh filter before placing back into proper storage container.



LOCTITE®

3860™

HDT180 HIGH TEMPERATURE
PHOTOPLASTIC
BLACK



NOTE

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of **Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark Usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.



LOCTITE®



FIND OUT MORE AT

LOCTITEAM.COM

LOCTITE®

Henkel Corporation

loctite3dp@henkel.com

